







Specifications (continued)	
	Crusher Run Subbase
	➤ WYDOT 803.4
	➤ Crusher run base or subbase materials
	➤ Gradation – maximum size only
	<small>Section 4 - 4</small>

Specifications (continued)	
	Crushed Subbase
	➤ WYDOT (803.4.2)
	➤ Shall meet R-Value specified ≥ 60
	➤ Fractured Faces $\geq 40\%$
	➤ AASHTO T96 ≤ 50
	➤ Liquid Limit ≤ 25
	➤ Plasticity Index ≤ 6
	➤ Gradation Requirements; Table 803.4.4-1
	➤ Aggregate Properties; Table 803.4.4-2
	➤ Soundness loss, no specification
	<small>Section 4 - 5</small>

Specifications (continued)	
	Crushed Base
	➤ WYDOT 803.4.3
	➤ Shall have no moisture sensitivity of the R-Value (R-Value at 200 PSI exudation cannot be more than 5 less than R-Value at 300 PSI)
	➤ Gradation
	➤ Five available: J, GR, L, K, W
	➤ Selected based on use, cost, conservation of materials
	➤ Most common: Subbase – Grading J; Base – Grading W and L
	<small>Section 4 - 6</small>

Specifications (continued)

Crushed Base (continued)

- **Coarse Aggregate**
 - ▶ Hard, durable particles
 - ▶ Fractured Faces ≥ 50%
 - ▶ AASHTO T 96 < 50%
 - ▶ Minimum R-Value ≥ 75
 - ▶ Soundness loss ≤ 18
- **Fine Aggregate**
 - ▶ L.L. ≤ 25
 - ▶ P.I. ≤ 3

Section 4 - 7

Specifications (continued)

**Crushed Base (Gravel Roads)
WYDOT 803.4**

Coarse Aggregate Fine Aggregate

- ▶ Hard, durable particles ▶ L.L. ≤ 30
- ▶ AASHTO T 96 ≤ 50% ▶ P.I. ≤ 4-12
- ▶ Minimum R-Value ≥ 60
- ▶ Soundness loss ≤ 18
- **Table 803.4.4-1: Gradation Requirements**
- Frequently require that the sum of the % passing the #200 plus the PI be between 15 & 20 (for binding)

Section 4 - 8

Table 803.4.4-1

Gradation Requirements: Subbase and Base

Sieve	Grading				
	J	GR	L	K	W
	% Passing				
2 in	100	-	-	-	-
1 1/2 in	90-100	-	100	100	100
1 in	-	100	90-100	90-100	100
3/4 in	-	90-100	-	-	-
1/2 in	-	65-85	60-85	-	60-85
3/8 in	-	-	-	-	-
No. 4	35-75	50-78	35-55	40-65	45-65
No. 8	-	37-67	25-50	30-55	33-53
No. 30	-	13-35	10-30	-	-
No. 200	0-15	4-15	3-15	3-15	3-12

Section 4 - 9

Table 803.4.4-2

Aggregate Properties: Subbase and Base

Properties	Subbase	Crushed Base	Crushed Base (Gravel Roads)
LA Abrasion maximum loss, %	50	50	50
Liquid Limit, maximum	25	25	30
Plasticity Index	0-6	0-3	4-12
R-Value, minimum	60	75	60
Soundness (MgSO4) loss for coarse aggregate, max.	-	18	18

Section 4 - 10

Specifications (continued)

Pit Run Filler

➤ **WYDOT 803.5.2**

➤ **When specified use non-plastic granular pit run filler consisting of granular materials. Ensure that 100 percent passes through a 3/8 in [9.5 mm] sieve and from 90 to 100 percent passes a No. 4 [4.75 mm] sieve. Stockpile in its own pile.**

Section 4 - 11

Specifications (continued)

Reclaimed Asphalt Pavement

➤ **WYDOT 803.5.3**

➤ **Crush and screen reclaimed asphalt pavement (RAP) greater than 2 in [50mm] so all material is prepared for recycling and a uniform mixture is maintained. Handle, screen and crush material so as not to produce unnecessary fractured aggregate or cause undue degradation.**

➤ **Ensure 100% of RAP used passes through a 2 in sieve**

Section 4 - 12

- 1 Update to new spec
Wesley Bybee, 12/23/2021

	Specifications (continued)
	Recycled Plant Mix Pavement
	<ul style="list-style-type: none">➤ WYDOT 803.5.4➤ Ensure that the combined virgin aggregate gradation meets the narrow band specifications developed during the mix design
	<small>Section 4 - 13</small>

	Specifications (continued)
	Plant Mix Base
	<ul style="list-style-type: none">➤ General Discussion Special Provisions for Specification➤ Gradation – Grading W unless noted on plans➤ Rarely used anymore due to cost
	<small>Section 4 - 14</small>

	Specifications (continued)
	Cement Treated Base
	<ul style="list-style-type: none">➤ General Discussion Special Provisions for Specifications➤ Coarse Aggregate – same as Crushed Base➤ Fine Aggregate – same as Crushed Base➤ Gradation – Special, less restrictive, more fines➤ Rarely used anymore due to propensity for transverse cracking
	<small>Section 4 - 15</small>

Specifications (continued)	
Asphalt Concrete – PMP	
<ul style="list-style-type: none"> ➤ WYDOT 803.5 ➤ Shall consist of crushed stones, crushed gravel or natural gravel <ul style="list-style-type: none"> ▶ Uniform quality; crushed; sound, tough, durable particles ▶ Coarse and Fine Aggregates shall be stockpiled in separate piles. ▶ Pit Run Filler (if used) is stockpiled separately. 	
<small>Section 4 - 16</small>	

Specifications (continued)	
Asphalt Concrete – PMP (continued)	
<ul style="list-style-type: none"> ➤ Aggregate ➤ Types <ul style="list-style-type: none"> ▶ Five Types: Table 803.5.5-2 ➤ Gradation <ul style="list-style-type: none"> ▶ Four available; Table 803.5.5-1 ▶ Selected based on use, cost, and conservation of materials 	
<small>Section 4 - 17</small>	

Table 803.5.5-1				
Gradation Requirements: Marshall and Superpave Mixes				
Sieve	% Passing, Nominal Maximum Size			
	1 in	3/4 in	1/2 in	3/8 in
1 1/4 in	100	-	-	-
1 in	90-100	100	-	-
3/4 in	65-90	90-100	100	-
1/2 in	50-85	55-90	90-100	100
3/8 in	40-75	45-85	55-90	90-100
No. 4	30-60	30-65	35-70	45-85
No. 8	20-45	20-50	20-55	30-65
No. 30	5-25	5-30	5-35	10-40
No. 200	2-7	2-7	2-7	2-7
<small>Section 4 - 18</small>				

Table 803.5.5-2

Aggregate Properties, Flexible Pavements

Properties	Agg I	Agg II	Agg III	Agg IV	Agg V
LA Abrasion maximum loss, %	35	40	40	40	40
Flat and Elongated (1 to 5 ratio) maximum, %	10	10	10	10	
Sand Equivalent minimum ⁽²⁾	45	45	45	40	40
Fractured Faces minimum ⁽¹⁾	95/90	95/90	85/80	75/-	55/-
Fine Aggregate Angularity minimum ⁽²⁾	45	45	45	40	40
Plasticity Index ⁽²⁾	NP	NP	NP	NP	NP
Soundness (MgSO ₄) maximum loss, % ⁽³⁾	18	18	18	18	18

⁽¹⁾ "95/90" denotes that 95 percent of the coarse aggregate has one or more fractured faces and 90 percent has two or more fractured faces.
⁽²⁾ Based on the minus No. 4 (4.75 mm) fraction of the composite blend.
⁽³⁾ Soundness (MgSO₄) will be tested on coarse aggregate.

Section 4 - 19

Specifications (continued)

Plant Mix Wearing Course

- **WYDOT 803.6**
- **Shall be crushed stone or gravel**
- **Shall meet the requirements for Agg I in Table 803.5.5-2**
- **Gradation – Table 803.6.1-1**

Section 4 - 20

Table 803.6.1-1

Gradation Requirements: Plant Mix Wearing Course

Sieve	% Passing
½ in	100
3/8 in	97-100
No. 4	25-45
No. 8	10-25
No. 200	2-7

Section 4 - 21

Specifications (continued)

Polish Resistant Aggregate

- > WYDOT 803.6.2
- > Limestone aggregates tend to polish when subjected to medium-to-high traffic levels.
- > When specified on the plans, provide aggregate that meets one of the requirements in Table 803.6.2-1

Section 4 - 22

Table 803.6.2-1

Polish Resistant Aggregate Requirements

Test Method	Description	Specification
AASHTO T279	9 hour (Polish Value), minimum	32
AASHTO T242	Skid Number, minimum ⁽¹⁾	40

(1) Base the skid number on historical skid numbers accumulated for a period of at least five years for a pavement that has carried traffic exceeding 3,500,000 accumulated 18-kip equivalent single axle loads.

Section 4 - 23

Specifications (continued)

Micro Surfacing

- > WYDOT 803.7
- > Used for filling transverse & longitudinal pavement depressions (rutting)
- > Mineral aggregate shall be 100% crushed.
- > A minimum of 95% of aggregate shall be retained on 1/2 in sieve
- > Sand equivalent ≥ 65%
- > When specified on the plans, provide aggregate that meets one of the requirements of Table 803.6.2-1

Section 4 - 24

Specifications (continued)	
Micro Surfacing (continued)	
<ul style="list-style-type: none"> ➤ L.A. abrasion loss ≤ 30% ➤ Contractor shall supply information on aggregate properties and JMF ➤ Gradation Table 803.7-1 	
Section 4 - 25	

Table 803.7-1	
Gradation Requirements: Micro Surfacing	
Sieve	% Passing
3/8 in	100
No. 4	70-90
No. 8	45-70
No. 16	28-50
No. 30	19-34
No. 50	12-25
No. 100	7-18
No. 200	5-15
Section 4 - 26	

Specifications (continued)	
Concrete	
<ul style="list-style-type: none"> ➤ WYDOT 803.2.2 ➤ Coarse Aggregate <ul style="list-style-type: none"> ▶ Washed ▶ Crushed stone or gravel ▶ AASHTO M80 except deleterious materials, Table 803.2.2-1 ▶ AASHTO T 96 ≤ 40 ▶ Sodium Sulfate Loss ≤ 12% ▶ Gradation; Table 803.2.2-2 and Table 803.2.2-3 ▶ When specified on the plans, provide aggregate that meets one of the requirements in Table 803.6.2-1 	
Section 4 - 27	

Specifications (continued)	
Concrete (continued)	
<ul style="list-style-type: none"> ➤ WYDOT 803.2.1 ➤ Fine aggregate <ul style="list-style-type: none"> ▶ Washed ▶ AASHTO M6 except deleterious material (Table 803.2.1-1) ▶ Gradation, Table 803.2.1-2 	

Section 4 - 28

Table 803.2.2-1	
Deleterious Substance Limits Coarse Aggregate for Concrete	
Substance	Max. %, by weight [mass]
Shale or Coal	0.1
Clay Lumps	0.5
Material Passing a No 200 [75µm] sieve	2.0
Other deleterious substances such as friable, thin, elongated or laminated pieces	3.0
All deleterious substances combined	5.0

Section 4 - 29

Table 803.2.2-3			
Gradation Requirements: Coarse Aggregate for Concrete			
Sieve	Classes A & B	(1) Class S	(1) PCCP
2 ½ in	-	-	-
2 in	-	-	-
1 ½ in	100	-	100
1 in	95-100	100	95-100
¾ in	-	90-100	-
½ in	25-60	-	25-60
3/8 in	-	20-55	-
No. 4	0-10	0-10	0-10
No. 8	0-5	0-5	0-5
No. 200	0-2	0-2	0-2

(1) For these, and for class A concrete used for pavement, ensure that at least 50 percent of the material retained on the No. 4 [4.75 mm] sieve has at least one fractured face.

Section 4 - 30

Table 803.2.1-1

Deleterious Substance Limits: Fine Aggregate for Concrete

Substance	Max. %, by weight [mass]
Clay Lumps	1.0
Coal and Lignite	1.0
Material Passing a No. 200 sieve	4.0

Section 4 - 31

Table 803.2.1-2

Gradation Requirements: Fine Aggregate for Concrete

Sieve	% Passing
3/8 in	100
No. 4	95-100
No. 16	45-80
No. 50	10-30
No. 100	2-10
No. 200	0-4

Section 4 - 32

Specifications (continued)

Chip Seal Aggregate

- WYDOT 803.8
- 2 different types;
- Table 803.8-1 for gradations requirements
- Table 803.8-2 for aggregate properties

Section 4 - 33

Table 803.8-1

**Table 803.8-1
Gradation Requirements: Chip Seal**

Sieve	% Passing	
	Type	
	B	C
1 in [25.0 mm]	–	–
¾ in [19.0 mm]	100	–
½ in [12.5 mm]	95 to 100	100
¾ in [9.5 mm]	40 to 70	80 to 100
No. 4 [4.75 mm]	0 to 15	0 to 10
No. 8 [2.36 mm]	0 to 7	0 to 5
No. 200 [75 µm]	0 to 2	0 to 2

Section 4 - 34

Table 803.8-2

**Table 803.8-2
Aggregate Properties: Chip Seal**

Property	Test Method	Specification
LA Abrasion loss, max., %	AASHTO T96	35
Flat and elongated (1:5 ratio), max. ⁽¹⁾ , %	ASTM D4791 (Method A)	10
Fractured Faces, min. ⁽²⁾ , %	AASHTO T335	95/90
Plasticity Index ⁽³⁾	AASHTO T90	NP
Polish Resistance	When specified, comply with Table 803.6.2-1	

⁽¹⁾ Flat and elongated will be tested on coarse aggregate (plus No. 4 [4.75 mm] fraction).

⁽²⁾ Percentage designation such as "95/90" denotes 95 percent of the coarse aggregate has one or more fractured faces and 90 percent has two or more fractured faces.

⁽³⁾ Based on minus No. 4 [4.75 mm] fraction of composite blend.

Section 4 - 35

Specifications (continued)

Aggregate for Bed Course Materials

➤ **WYDOT 803.10**

➤ **Provide and use aggregate consisting of sand, gravel, crushed stone and other approved materials which 100 percent passes through a ½ in sieve**

Section 4 - 36

Specifications (continued)

Gravel for Drains

>WYDOT 803.11
 >Use aggregate that is crushed or natural sand and gravel or other free-draining materials approved by the engineer and that meets the requirements of Table 803.11-1

Section 4 - 37

Table 803.12-1

Gradation Requirements: Gravel for Drains

Table 803.11-1
Gradation Requirements: Gravel for Drains

Sieve	% Passing Grading B
2 in [50 mm]	-
1½ in [37.5 mm]	100
1 in [25.0 mm]	95 to 100
¾ in [19.0 mm]	-
½ in [9.5 mm]	-
No. 4 [4.75 mm]	0 to 10
No. 8 [2.36 mm]	-
No. 16 [1.18 mm]	-
No. 100 [150 µm]	-

Section 4 - 38

Specifications (continued)

Aggregate for Maintenance Stockpiles

>WYDOT 803.12
 >Type A, B and C

Section 4 - 39

Specifications (continued)

Type A

- Stockpile aggregate consisting of clean, hard, durable particles of gravel or sand
- Percentage of wear ≤ 40

Section 4 - 40

Specifications (continued)

Type A (continued)

- Ensure 95% of material is retained on sieve before crushing
- For the fraction passing No. 4 sieve, ensure liquid limit ≤ 25 and plasticity index ≤ 3
- Table 803.12.1-1

Section 4 - 41

Table 803.12.1-1

Gradation Requirements: Maintenance Stockpiles (Type A)

Sieve	% Passing, Nominal Maximum Size	
	1/2 in	3/8 in
3/4 in	100	-
1/2 in	90-100	100
3/8 in	60-90	90-100
No. 4	45-60	50-80
No. 8	30-50	33-63
No. 200	3-12	3-12

Section 4 - 42

Specifications (continued)	
Type B	
<p>➤ Stockpile aggregate consisting of clean, hard particles of crusher- run gravel or screened stone obtained from designated portions of the pit.</p> <p>➤ Ensure Plasticity Index ≤ 3</p> <p>➤ Table 803.12.2-1</p>	

Section 4 - 43

Table 803.12.2-1					
Gradation Requirements: Maintenance Stockpiles (Type B)					
Sieve	% Passing				
	3/4 in	1/2 in	3/8 in	No. 4	No. 4 modified
1 in	100	-	-	-	-
3/4 in	95-100	100	-	-	-
1/2 in	-	95-100	100	-	-
3/8 in	-	-	95-100	100	100
No. 4	0-75	0-75	0-75	95-100	95-100
No. 200	0-15	0-15	0-15	0-5	0-12

Section 4 - 44

Specifications (continued)	
Type C	
<p>➤ Stockpile aggregate consisting of crusher-run scoria meeting requirements of Table 803.12.3-1</p>	

Section 4 - 45

Table 803.12.3-1

Gradation Requirements: Maintenance Stockpiles (Type C)

Sieve	% Passing
3/8 in	100
No. 4	85-100
No. 200	0-10

Section 4 - 46

Specifications (continued)

Aggregate for Pervious Backfill Material

- WYDOT 803.13
- Use nonplastic aggregate consisting of crushed gravel, crushed rock, manufactured sands or combinations thereof.
- Ensure liquid limit is ≤ 30

Section 4 - 47

Specifications (continued)

Aggregate for Pervious Backfill Material (continued)

- For reinforced bridge approach fills, ensure materials used have an internal friction angle of at least 35 degrees (another way of requiring some degree of fracture)
- Table 803.13-1

Section 4 - 48

Table 803.13-1

**Gradation Requirements:
Pervious Backfill Material**

Sieve	% Passing
2 in	100
No. 4	0 to 50
No. 30	0 to 35
No. 100	0 to 10
No. 200	0 to 4

Section 4 - 49

Specifications (continued)

Aggregate for Riprap

➤ **WYDOT 803.14**

➤ **Use aggregate consisting of hard, durable, crushed, quarried, or natural stone or broken concrete.**

➤ **Ensure specific gravity of at least 2.4, absorption no greater than 4%, pieces are free of weak lamination and cleavages and at least 60% weigh 77 lbs.**

Section 4 - 50

Specifications (continued)

Aggregate for Riprap (continued)

➤ **Do not provide material that will disintegrate in water or weather**

➤ **Aggregate size, Table 803.14-1**

➤ **Aggregate weight, Table 803.14-2**

Section 4 - 51

Table 803.14-1

**Table 803.14-1
Gradation Requirements: Minimum and Maximum Aggregate Size**

Class	Nominal Size in (mm)	d15 ⁽¹⁾		d50 ⁽²⁾		d85 ⁽³⁾		d100 ⁽⁴⁾	
		Min in (mm)	Max in (mm)	Min in (mm)	Max in (mm)	Min in (mm)	Max in (mm)	Min in (mm)	Max in (mm)
I	6 [150]	3.7 [92]	5.2 [130]	5.7 [142]	6.9 [172]	7.8 [195]	9.2 [230]	12 [300]	
II	9 [225]	5.5 [137]	7.8 [195]	8.5 [212]	10.5 [262]	11.5 [287]	14 [350]	18 [450]	
III	12 [300]	7.3 [182]	10.5 [262]	11.5 [287]	14 [350]	15.5 [387]	18.5 [462]	24 [600]	
IV	15 [375]	9.2 [230]	13 [325]	14.5 [362]	17.5 [437]	19.5 [487]	23 [575]	30 [750]	
V	18 [450]	11 [275]	15.5 [387]	17 [425]	20.5 [512]	23.5 [587]	27.5 [687]	36 [900]	
VI	21 [525]	13 [325]	18.5 [462]	20 [500]	24 [600]	27.5 [687]	32.5 [812]	42 [1050]	
VII	24 [600]	14.5 [362]	21 [525]	23 [575]	27.5 [687]	31 [775]	37 [925]	48 [1200]	
VIII	30 [750]	18.5 [462]	26 [650]	28.5 [712]	34.5 [862]	39 [975]	46 [1150]	60 [1500]	

⁽¹⁾ 15% of the aggregate will be smaller than min size shown.
⁽²⁾ 50% of the aggregate will be smaller than min size shown.
⁽³⁾ 85% of the aggregate will be smaller than min size shown.
⁽⁴⁾ Maximum aggregate size.

Section 4 - 52

Table 803.14-2

**Table 803.14-2
Gradation Requirements: Minimum and Maximum Aggregate Weight**

Class	Nominal Weight lbs [kg]	W15 ⁽¹⁾		W50 ⁽²⁾		W85 ⁽³⁾		W100 ⁽⁴⁾	
		Min lbs [kg]	Max lbs [kg]	Min lbs [kg]	Max lbs [kg]	Min lbs [kg]	Max lbs [kg]	Min lbs [kg]	Max lbs [kg]
I	20 [9]	4 [1]	12 [5]	15 [6]	27 [12]	39 [17]	64 [29]	140 [63]	
II	60 [27]	13 [5]	39 [17]	51 [23]	90 [40]	130 [58]	220 [99]	470 [213]	1100 [495]
III	150 [68]	32 [14]	93 [42]	120 [54]	210 [95]	310 [140]	510 [231]	1100 [495]	
IV	300 [136]	62 [28]	180 [81]	240 [108]	420 [190]	600 [272]	1000 [453]	2200 [997]	
V	500 [226]	110 [49]	310 [140]	410 [185]	720 [326]	1050 [476]	1750 [793]	3800 [1723]	
VI	750 [340]	170 [77]	500 [226]	650 [294]	1150 [521]	1650 [748]	2800 [1270]	6000 [2721]	
VII	1000 [453]	260 [117]	740 [335]	950 [430]	1700 [771]	2500 [1134]	4100 [1859]	9000 [4082]	
VIII	2000 [907]	500 [226]	1450 [657]	1900 [861]	3200 [1496]	4800 [2177]	8000 [3628]	17600 [7983]	

⁽¹⁾ 15% of the aggregate will be smaller than min weight shown.
⁽²⁾ 50% of the aggregate will be smaller than min weight shown.
⁽³⁾ 85% of the aggregate will be smaller than min weight shown.
⁽⁴⁾ Maximum aggregate weight.

Section 4 - 53

Specifications (continued)

Filter Aggregate for Riprap 803.14.7

- Use aggregate consisting of hard, durable particles or fragments of crushed stone or natural gravel, screened or crushed

- Table 803.14.7-1

Section 4 - 54

Table 803.14.7-1

Table 803.14.7-1
Gradation Requirements: Riprap Filter Aggregate

Sieve	% Passing
3 in [75 mm]	100
No. 4 [4.75 mm]	20 to 50
No. 200 [75µm]	0 to 10

Section 4 - 55

Specifications (continued)

Aggregate for Flowable Backfill

- Use nonplastic aggregate with a liquid limit ≤ 25
- WYDOT 803.15
- Table 803.15-1

Section 4 - 56

Table 803.15-1

**Gradation Requirements:
Flowable Backfill**

Sieve	% Passing
3/4 in	100
No. 200	2 to 10

Section 4 - 57

28

14.7

Wesley Bybee, 12/23/2021