



AGGREGATES

Section 5 – Developing A Job Mix Formula (JMF)

Section 5 - 1

Developing a Job Mix Formula

The actual calculations in this section will not be on the exam but you would need to have an appreciation to the process. In addition, you would need to be able to answer general questions about the process.

Section 5 - 2

Developing A JMF

- **JMF – The optimum combination of materials meeting all mix design and specification requirements**
- **Two parts (minimum)**
 - Gradation established by blending
 - Asphalt Content – Mix Design
 - Adjustment of blends if mix design doesn't meet all requirements.

Section 5 - 3

Trial and Error Method	
<ul style="list-style-type: none"> ➤ Step 1 – Gather Data <ul style="list-style-type: none"> ▶ Gradation of each aggregate <ul style="list-style-type: none"> ◆ AASHTO T 11 & T 27 ▶ Specification Tolerances ➤ Step 2 – Select Target Values <ul style="list-style-type: none"> ▶ Center of Limits As a Starting Point 	

Section 5 - 4

Trial and Error Method (continued)	
<ul style="list-style-type: none"> ➤ Step 3 – Make a Guess <ul style="list-style-type: none"> ▶ Select Percentages of Each ▶ Start with Control Sieves; #4, #200 ➤ Step 4 – Perform Calculation <ul style="list-style-type: none"> ▶ <i>Multiply selected % x % passing each sieve</i> ▶ <i>Add amounts from each material</i> 	

Section 5 - 5

Trial and Error Method (continued)	
<ul style="list-style-type: none"> ➤ Step 5 – Compare With Target Values <ul style="list-style-type: none"> ▶ Compare each sieve ▶ Determine adjustment to meet target ➤ Step 6 – Repeat To Find Optimum 	

Section 5 - 6

Example 1a

Material Percent Used	AGG #1		AGG #2		Combined Gradation	Target Value	Specification Limits
	U.S. Sieves	Percent Passing	Percent Batch	Percent Passing			
3/8"	100		100				100
No. 4	90		100				80-100
No. 8	30		100				65-100
No. 16	7		88				40-80
No. 30	3		47				20-65
No. 50	1		32				7-40
No. 100	0		24				3-20
No. 200	0		10				2-10

Section 5 - 7

Example 1b

Material Percent Used	AGG #1 50%		AGG #2 50%		Combined Gradation	Target Value	Specification Limits
	U.S. Sieves	Percent Passing	Percent Batch	Percent Passing			
2"							
1.5"							
1"							
3/4"							
1/2"							
3/8"	100						100 100
No. 4	90						90 80-100
No. 8	30		100				83 65-100
No. 16	7		88				60 40-80
No. 30	3		47				43 20-65
No. 50	1		32				23 7-40
No. 100	0		24				12 3-20
No. 200	0		10				6.0 2-10

Section 5 - 8

Example 1c

Material Percent Used	AGG #1 50%		AGG #2 50%		Combined Gradation	Target Value	Specification Limits
	U.S. Sieves	Percent Passing	Percent Batch	Percent Passing			
3/8"	100	50	100	50	100	100	100
No. 4	90	45	100	50	95	90	80-100
No. 8	30	15	100	50	65	83	65-100
No. 16	7	3.5	88	44	47.5	60	40-80
No. 30	3	1.5	47	23.5	25	43	20-65
No. 50	1	0.5	32	16	16.5	23	7-40
No. 100	0		24	12	12	12	3-20
No. 200	0		10	5.0	5.0	6.0	2-10

Section 5 - 9

Example 1d

Material Percent Used	AGG #1		AGG #2		Combined Gradation	Target Value	Specification Limits
	30%		70%				
U.S. Sieves	Percent Passing	Percent Batch	Percent Passing	Percent Batch			
3/8"	100	30	100	70	100 ^v	100	100
No. 4	90	27	100	70	97 ^v	90	80-100
No. 8	30	9	100	70	79 ^v	83	65-100
No. 16	7	2.1	88	61.6	63.7 ^v	60	40-80
No. 30	3	0.9	47	32.9	33.8 ^v	43	20-65
No. 50	1	0.3	32	22.4	22.7 ^v	23	7-40
No. 100	0	-	24	16.8	16.8 ^v	12	3-20
No. 200	0	-	10	7.0	7.0 ^v	6.0	2-10

Section 5 - 10

Example 1e

Material Percent Used	AGG #1		AGG #2		Combined Gradation	Target Value	Specification Limit
	35%		65%				
U.S. Sieves	Percent Passing	Percent Batch	Percent Passing	Percent Batch			
3/8"	100	35	100	65	100 ^v	100	100
No. 4	90	31.5	100	65	96.5 ^v	90	80-100
No. 8	30	10.5	100	65	75.5 ^v	83	65-100
No. 16	7	2.4	88	57.2	59.6 ^v	60	40-80
No. 30	3	1.0	47	30.5	31.5 ^v	43	20-65
No. 50	1	0.3	32	20.8	21.1 ^v	23	7-40
No. 100	0	-	24	15.6	15.6 ^v	12	3-20
No. 200	0	-	10	6.5	6.5 ^v	6.0	2-10

Section 5 - 11

Example 2a

Material Percent Used	Crushed Gravel		Crushed Sand #2		Fine Sand #3		Filler		Combined Gradation	Target Value	Specification Limits
	Percent Passing	Percent Batch	Percent Passing	Percent Batch	Percent Passing	Percent Batch	Percent Passing	Percent Batch			
1.5"	100									100	100
1"	93									95	80-100
1/2"	54		100							70	60-80
No. 4	5		99		100					43	25-60
No. 8	1		94		90					30	15-45
No. 50	0		12		65		100			11	3-18
No. 200	0		1.0		12		80			4.0	1-7

Section 5 - 12

Example 2b

Material Used	Crushed Gravel #1 68%		Crushed Sand #2 14%		Fine Sand #3 15%		Filler 3%		Combined Gradation	Target Value	Specification Limits
	U.S. Sieves	Percent Passing	Percent Batch	Percent Passing	Percent Batch	Percent Passing	Percent Batch	Percent Passing			
1.5"	100	68	100	14	100	15	100	3	100 ^a	100	100
1"	99	63.2	100	14	100	15	100	3	95.2 ^b	95	90-100
3/4"									1		
1/2"	54	36.7	100	14	100 ^c	15	100	3	68.7 ^d	70	60-80
3/8"											
No. 4	5	3.4	99	13.9	100	15	100	3	35.3 ^e	43	25-60
No. 8	1	0.7	94	13.2	90	13.5	100	3	30.4 ^f	30	15-45
No. 16											
No. 30											
No. 50			12	1.7	65	9.8	100	3	14.5 ^g	11	3-18
No. 100											
No. 200			1.0	0.1	12	1.8	80	2.4	4.3 ^h	4	1-7

Section 5 - 13
