

ASPHALT BINDER

Section 3 – Aggregates For PMP

Physical Properties

- **Texture**
- **Gradation**
- **Absorption**

Texture

- **Definition – Appearance**
- **Function of shape**
- **Shape**
 - ▶ **Angular**
 - ▶ **Rounded**
 - ▶ **Bulky**
 - ▶ **Flat / Elongated**

Gradation

- **Size**
 - ▶ **Fractionation**
 - ▶ **Gradation**

- **Uniform**

- **Well**


- **Gap**

- **Open**

Particle Size

- ▶ **Fractionation**
- ▶ **Gradation**

Aggregate Gradation



Gradation

- **Nominal maximum Size: One sieve size larger than the first sieve to retain more than 10 percent**
- **Maximum Size: one sieve size larger than nominal maximum size.**

Absorption

- **Surface Porosity**
 - ▶ **Hydrophobic – repels**
 - ▶ **Hydrophylic – attracts**

- **High Absorption = High % Binder**
 - ▶ **AFFINITY FOR ASPHALT**

- **Mechanical**
 - ▶ **Absorption**

- **Chemical**
 - ▶ **Asphalt / Aggregate**

- **Stripping**

Aggregate Tests

- **Coarse aggregate angularity**
- **Fine aggregate angularity**
- **Flat and elongated particles**
- **Clay content**
- **Soundness**
- **Durability**
- **Deleterious materials**

ASTM D 5821

(Coarse Aggregate Angularity)

- **ASTM D 5821 – Standard Test Method for Determining the Percentage of Fractured Particles in Coarse Aggregate**
- **Summary: The percentage of aggregate larger than #4 with one or more fractured faces is determined**
- **Significance: Internal friction of coarse aggregate affect the workability, consolidation, strength, stability, and VMA of asphalt mixes. More fractured faces will result in a higher internal friction.**

AASHTO T 304

(Fine Aggregate Angularity)

- **AASHTO T 304 (Method A) – Standard Test Method for Uncompacted Void Content of Fine Aggregate (MTM 824.0)**
- **Summary:** The void content of a loose sample of #8 to #100 fine aggregate is determined as a percent of the original mass.
- **Significance:** Void content is influenced by particle shape, texture and gradation. It can be an indicator of: water demand in concrete; flowability or workability; influence of fine aggregate on VMA; and bituminous concrete stability


ASTM D4791

(Flat and Elongated Particles)

ASTM D4791 – Flat and Elongated Particles in Coarse Aggregate (MTM 835.0)

- **Summary:** Individual particles of aggregate are measured to determine the ratio of length to thickness.
- **Significance:** Flat and elongated particles affect workability and consolidation and may indicate degradation.
- **Influenced by crushing method & aggregate mineralogy.**

Measuring Flat & Elongated Particles




AASHTO T 176 (Clay Content)

AASHTO T 176: Plastic Fines in Graded Aggregates and Soils by Use of the Sand Equivalent Test (MTM 836.0)

- **Summary:** A sample of fine aggregate is mixed with a flocculating solution in a graduated cylinder. The cylinder height of suspended clay and sedimented sand is measured.
- **Significance:** Clay content would affect the aggregate surface area and the asphalt content

Sand Equivalent Test



AASHTO T 96 (Durability)

AASHTO T 96 – Resistance to Degradation by Abrasion and Impact in the Los Angeles Machine (MTM 818.0) 2004

- **Summary:** A sample of coarse aggregate is placed in a steel drum along with a certain number of steel spheres. The drum is rotated 500 times and the sample is then washed over a #12 sieve. The difference in mass between initial and final mass is the % loss
- **Significance:** Abrasion loss is related to aggregate quality or durability.

AASHTO T 104 (Soundness)

AASHTO T 104: Soundness of Aggregate by Use of Sodium Sulfate or Magnesium Sulfate

- **Summary:** An aggregate sample is exposed to repeated immersions in saturated solutions of sodium or magnesium sulfate followed by oven drying.
- **Significance:** The percent loss over various sieves is related to the freeze/thaw resistance of the aggregate.

AASHTO T 112 (Deleterious Material)

AASHTO T 112: Clay Lumps and Friable Particles in Aggregate

- **Summary:** Wet sieving aggregate size fractions over specified sieves. The percentage of mass lost is reported as the percentage of clay lumps.
- **Significance:** The percent to clay lumps will affect the optimum asphalt content and the performance of the asphalt mix.

Crushing and Stockpiling

- **Material up to 18” processed**

- **Separate Stockpiles**
 - ▶ **Coarse Aggregate – Retained on #4**
 - ▶ **Fine Aggregate – Passing #4**
 - ▶ **Pit Run Filler**

- **Stockpiling**

Specifications

Asphalt Binder– PMP

- **WYDOT Standard Specifications 803.5**
- **Shall consist of crushed stones, crushed gravel or natural gravel**
 - ▶ **Uniform quality; crushed; sound, tough, durable particles**
 - ▶ **Coarse and Fine Aggregates shall be stockpiled in separate piles**
 - ▶ **Pit Run Filler in separate pile.**

Specifications (continued)

Asphalt Binder– PMP (continued)

- **Aggregate**
- **Gradation**
 - ▶ **Four available; Table 803.5.5-1**
 - ▶ **Selected based on use, cost, and conservation of materials**
- **Types**
 - ▶ **Five Types: Table 803.5.5-2**

Table 803.5.5-1

Gradation Requirements, Marshall and Superpave Mixes

Sieve	% Passing, Nominal Maximum Size			
	1 in	3/4 in	1/2 in	3/8 in
1 1/4 in	100	-	-	-
1 in	90-100	100	-	-
3/4 in	65-90	90-100	100	-
1/2 in	50-85	55-90	90-100	100
3/8 in	40-75	45-85	55-90	90-100
No. 4	30-60	30-65	35-70	45-85
No. 8	20-45	20-50	20-55	30-65
No. 30	5-25	5-30	5-35	10-40
No. 200	2-7	2-7	2-7	2-7

Table 803.5.5-2

Aggregate Properties, Flexible Pavements

Properties	Agg I	Agg II	Agg III	Agg IV	Agg V
LA Abrasio maximum loss, %	35	40	40	40	40
Flat and Elongated (1 to 5 ratio) maximum, %	10	10	10	10	-
Sand Equivalent minimum (2)	45	45	45	40	40
Fractured Faces minimum (1)	95/90	95/90	85/80	75/-	55/-
Fine Aggregate Angularity minimum (2)	45	45	45	40	40
Plasticity Index (2)	NP	NP	NP	NP	NP
Soundness (MgSO ₄) maximum loss %	18	18	18	18	18

(1) "95/90" denotes that 95 percent of the coarse aggregate has one or more fractured faces and 90 percent has two or more fractured faces.

(2) Based on the minus No. 4 fraction of the composite blend

Specifications (continued)

Plant Mix Wearing Course

- **WYDOT 803.6**
- **Shall be crushed stone or gravel**
- **Shall meet the requirements for Agg I in Table 803.5.5-2**
- **Gradation – Table 803.6.1-1**
- **When specified on the plans, provide aggregate that is in accordance with one of the requirements in Table 803.6.2-1, Polish Resistant Aggregate Requirements**

Table 803.6.1-1

Gradation Requirements, Plant Mix Wearing Course

Sieve	% Passing
1/2 in	100
3/8 in	97-100
No. 4	25-45
No. 8	10-25
No. 200	2-7

Table 803.6.2-1

Polish Resistant Aggregate Requirements

Test Method	Description	Specification
AASHTO T279	9 hour (Polish Value), minimum	32
AASHTO T 242	(1) Skid Number, minimum	40

- (1) Base the skid number on historical skid numbers accumulated for a period of at least five years for a pavement that has carried traffic exceeding 3,500,000 accumulated 18-kip equivalent single axel loads.

Specifications (continued)

Microsurfacing

- **Mineral aggregate shall be 100% crushed.**
- **Prior to crushing a minimum of 95% of aggregate shall be retained on 1/2 in sieve**
- **Sand equivalent $\geq 65\%$**
- **L.A. abrasion loss $\leq 30\%$**
- **Contractor shall supply information on aggregate properties and JMF**
- **Gradation Table 803.7-1**
- **When specified on the plans, provide aggregate that is in accordance with one of the requirements in Table 803.6.2-1, Polish Resistant Aggregate Requirements**

Table 803.7-1

Gradation Requirements, Microsurfacing

Sieve	% Passing
3/8 in	100
No. 4	70-90
No. 8	45-70
No. 16	28-50
No. 30	19-34
No. 50	12-25
No. 100	7-18
No. 200	5-15