



1



2



3

Pay Factor Determination (p. 15-4)

► Determine standard deviation (s)

$$s = \sqrt{\left(\frac{1}{n-1}\right) \sum (x - \bar{x})^2}$$

► Calculate the Quality Index (QI)

$$\text{Upper Quality Index} = Q_U = \frac{SL_U - \bar{x}}{s}$$

$$\text{Lower Quality Index} = Q_L = \frac{\bar{x} - SL_L}{s}$$

► Where:

$$SL_U = 100$$

$$SL_L = 92$$

$$n = 7$$

► For PF < 0.75 Remove and Replace

Section 15 - 4

4

Pay Factor Determination (p. 15-5) Table 113.1-1

Table 113.1-1 Quality Level Analysis by the Standard Deviation Method					
PU or PL percent Within Limits for Positive Values of QU or QL	Upper Quality Index QU or Lower Quality Index QL				
	n = 3	n = 4	n = 5	n = 6	n = 7
100	1.16	1.30	1.39	2.03	2.23
99	1.47	1.67	1.80	1.89	1.89
98	1.15	1.44	1.60	1.70	1.76
97	1.41	1.54	1.62	1.67	1.67
96	1.38	1.49	1.55	1.59	1.59
95	1.35	1.44	1.49	1.52	1.52
94	1.32	1.39	1.43	1.46	1.46
93	1.29	1.35	1.38	1.40	1.40
92	1.12	1.26	1.31	1.33	1.35
91	1.11	1.23	1.27	1.29	1.30
90	1.10	1.20	1.23	1.24	1.25
89	1.09	1.17	1.19	1.20	1.21
88	1.07	1.14	1.15	1.16	1.16
87	1.06	1.11	1.12	1.12	1.13
86	1.04	1.08	1.08	1.08	1.08
85	1.03	1.05	1.05	1.04	1.04
84	1.01	1.02	1.01	1.01	1.01
83	1.00	0.99	0.98	0.97	0.97
82	0.97	0.96	0.95	0.94	0.94
81	0.96	0.93	0.91	0.90	0.90
80	0.93	0.90	0.88	0.87	0.86
79	0.91	0.87	0.85	0.84	0.83
78	0.89	0.84	0.82	0.80	0.79
77	0.87	0.81	0.78	0.77	0.76
76	0.84	0.78	0.75	0.74	0.73
75	0.82	0.75	0.72	0.71	0.70
74	0.79	0.72	0.69	0.68	0.67
73	0.76	0.69	0.66	0.65	0.64

Section 15 - 5

5

Pay Factor Determination (p. 15-6) Table 113.1-1

Table 113.1-1 Quality Level Analysis by the Standard Deviation Method					
PU or PL percent Within Limits for Positive Values of QU or QL	Upper Quality Index QU or Lower Quality Index QL				
	n = 3	n = 4	n = 5	n = 6	n = 7
72	0.74	0.66	0.63	0.62	0.61
71	0.71	0.63	0.60	0.59	0.58
70	0.68	0.60	0.57	0.56	0.55
69	0.65	0.57	0.54	0.53	0.52
68	0.62	0.54	0.51	0.50	0.49
67	0.59	0.51	0.47	0.47	0.46
66	0.56	0.48	0.45	0.44	0.44
65	0.52	0.45	0.43	0.41	0.41
64	0.49	0.42	0.40	0.39	0.39
63	0.46	0.39	0.37	0.36	0.35
62	0.43	0.36	0.34	0.33	0.33
61	0.39	0.33	0.31	0.30	0.30
60	0.36	0.30	0.28	0.27	0.27
59	0.32	0.27	0.25	0.25	0.24
58	0.29	0.24	0.23	0.22	0.21
57	0.25	0.21	0.20	0.19	0.19
56	0.22	0.18	0.17	0.16	0.16
55	0.18	0.15	0.14	0.13	0.13
54	0.14	0.12	0.11	0.11	0.11
53	0.11	0.09	0.08	0.08	0.08
52	0.07	0.06	0.06	0.05	0.05
51	0.04	0.03	0.03	0.03	0.03
50	0.00	0.00	0.00	0.00	0.00

Note: If the value of QU or QL does not correspond exactly to a figure in the table, use the next highest figure. For values of QU or QL less than zero, use the absolute value of the calculated QU or QL to determine the corresponding value for PU or PL. The actual value of PU or PL equals 100 minus the table value for PU or PL.

Section 15 - 6

6

Pay Factor Determination (p. 15-7)

► Determine PWL(Density) (Quality Level)

$$\text{quality level} = (P_U + P_L) - 100$$

► Calculate the Pay Factor(Density)

$$PF_D = 0.55 + 0.50 \times \frac{PWL_D}{100}$$

► Where:

PF_D = pay factor for in-place density, rounded to the nearest 0.0001
 PWL_D = percent within limits for in-place density

Section 15 - 7

7

Compaction Pay Factors

1. 94.3%	95.80%	94.70%	95.00%	95.60%	95.2%	94.90%	$Q_u = 9.48$ $Q_l = 5.90$ $P_U = 100$ from Table (113.1-1) $P_L = 100$ from Table (113.1-1) Quality Level = 100 $PF_D = 1.05$
$x = 95.07$ $s = 0.52$							
2. 95.7%	92.90%	92.80%	92.00%	95.40%	93.60%	93.50%	$Q_u = 4.60$ $Q_l = 1.24$ $P_U = 100$ from Table (113.1-1) $P_L = 90$ from Table (113.1-1) Quality Level = 90 $PF_D = 1.0$
$x = 93.70$ $s = 1.37$							
3. 98.80%	98.2%	98.00%	98.90%	96.80%	92.30%	90.20%	$Q_u = 1.10$ $Q_l = 1.20$ $P_U = 87$ from Table (113.1-1) $P_L = 89$ from Table (113.1-1) Quality Level = 76 $PF_D = 0.93$
$x = 96.17$ $s = 3.48$							
4. 92.60%	90.70%	91.90%	93.40%	92.10%	91.00%	90.90%	$Q_u = 8.20$ $Q_l = -0.20$ $P_U = 100$ from Table (113.1-1) $P_L = 42$ Quality Level = 42 $PF_D = 0.76$
$x = 91.8$ $s = 1.00$							

Section 15 - 8

8

Cost Analysis

Example #1

Material	% of Total Mix	Cost/Ton
Aggregate #1	45	\$7.50
Aggregate #2	33	\$6.65
Aggregate #33	16	\$5.50
Asphalt	6	\$120

$45\% \times \$7.50$ or $0.45 \times 7.50 = 3.38$
 $33\% \times \$6.65$ or $0.33 \times 6.65 = 2.19$
 $16\% \times \$5.50$ or $0.16 \times 5.50 = 0.88$
 $6\% \times \$120$ or $0.06 \times 120 = 3.38$

\$13.65 per mix ton

Density = 155 pcf

Pavement Thickness = 4.5 inches

Compute the Following:

- Mix Cost per Ton $\frac{\$}{\text{yd}^3} = \frac{\$13.65}{\text{ton}} \times \frac{155 \text{ lb}}{\text{ft}^3} \times \frac{1 \text{ ton}}{2000 \text{ lb}} \times \frac{27 \text{ ft}^3}{\text{yd}^3} = \$28.56/\text{yd}^3$
- Cost per Cubic Yard
- Cost per Square Yard $\frac{\$}{\text{yd}^2} = \frac{\$28.56}{\text{yd}^3} \times 4.5 \text{ in} \times \frac{1 \text{ yd}}{36 \text{ in}} = \$3.57/\text{yd}^2$

Section 15 - 9

9

Cost Analysis

Example #2

Solution:

Mix Cost per Ton = \$25.00
Density = 150 pcf
Pavement Thickness = 5 in

Compute the Following:
1. Cost per Cubic Yard
2. Cost per Square Yard

$$\frac{\$}{yd^3} = \frac{\$25.00}{ton} \times \frac{150 lb}{ft^3} \times \frac{1 ton}{2000 lb} \times \frac{27 ft^3}{yd^3} = \$50.63/yd^3$$
$$\frac{\$}{yd^2} = \frac{\$50.63}{yd^3} \times 5.0 in \times \frac{1 yd}{36 in} = \$7.03/yd^2$$

Section 15 - 10

10

Table (MTM417.0) (p. 15-9)

Grading (Nominal Max. Size)					
	1"	3/4"	1/2"	3/8"	PMWC
Sieve	Allowable Difference (% Passing)				
1 1/4"	1.5				
1"	2	1.5			
3/4"	3	2	1.5		
1/2"	3.4	3	2	1.5	1.5
3/8"	3.4	3.4	3.4	2	2
No. 4	3.4	3.4	3.4	3.4	3.4
No. 8	3.3	3.3	3.3	3.3	3.3
No. 30	2.9	2.9	2.9	2.9	
No. 200	1.2	1.2	1.2	1.2	1.2

Section 15 - 11

11

Verification Testing (Aggregate Gradation)

Problem #1 See Section 9-33 Table (MTM417.0)

A Contractor Obtained the Following Gradation for an Aggregate Sample:
For 3/4" size 95% – 94% = 1% Ok (1≤ 2)
For 1/2" size 75% – 72% = 3% Ok (3≤ 3)
For 3/8" size 68% – 65% = 3% Ok (3≤ 3.4)
For #30 size 27% – 23% = 4% Fail (4> 2.9)
The DOT Performed the verification testing on the Corresponding Sample and Obtained the Following Results:

If any fail, see required steps on page 9-32

Assuming that PMP %" w Results can be used for

Grading (Nominal Max. Size)					
	1"	3/4"	1/2"	3/8"	PMWC
Sieve	Allowable Difference (% Passing)				
1 1/4"	1.5				
1"	2	1.5			
3/4"	3	2	1.5		
1/2"	3.4	3	2	1.5	1.5
3/8"	3.4	3.4	3.4	2	2
No. 4	3.4	3.4	3.4	3.4	3.4
No. 8	3.3	3.3	3.3	3.3	3.3
No. 30	2.9	2.9	2.9	2.9	
No. 200	1.2	1.2	1.2	1.2	1.2

Sieve Size	% Passing
1"	100
3/4"	95
1/2"	75
3/8"	68
#4	52
#8	41
#30	27
#200	5.2

Sieve Size	% Passing
1"	100
3/4"	94
1/2"	72
3/8"	65
#4	50
#8	39
#30	23
#200	4.8

Section 15 - 12

12

4

Verification Testing (Aggregate Gradation)

Problem #2

A Contractor Obtained the Following Gradation for an Aggregate Sample:

Sieve Size	% Passing
1/2"	100
3/8"	96
#4	52
#8	39
#30	17
#200	4.2

The DOT Performed the verification testing on the Corresponding Sample and Obtained the Following Results:

Sieve Size	% Passing
1/2"	100
3/8"	99
#4	56
#8	43
#30	21
#200	6.1

Assuming that PMP 3/8" was used, Determine if the contractor's Test Results can be used for Calculating the Pay Factor.

Section 15 - 13

13

Verification Testing (Aggregate Gradation)

Problem #3

A Contractor Obtained the Following Gradation for an Aggregate Sample:

Sieve Size	% Passing
3/4"	100
1/2"	96
3/8"	79
#4	61
#8	48
#30	26
#200	4.5

The DOT Performed the verification testing on the Corresponding Sample and Obtained the Following Results:

Sieve Size	% Passing
3/4"	100
1/2"	94
3/8"	78
#4	59
#8	46
#30	25
#200	4.2

Assuming that PMP 1/2" was used, Determine if the contractor's Test Results can be used for Calculating the Pay Factor.

Section 15 - 14

14

Verification Testing (Density)

The Following Densities Were Obtained from Verification Testing. Determine Which Sets Confirm the Contractor's Results.

Contractor's Density	DOT's Density	Difference	Difference Acceptable	Difference Unacceptable
141.2	141.9	0.7 pcf	X	
142.3	142.1	0.2 pcf	X	
142.5	141.3	1.2 pcf	X	
143.5	141.1	2.4 pcf		X
141.3	144.5	3.2 pcf		X
143.1	142.9	0.2 pcf	X	
144.9	143.7	1.2 pcf	X	
142.3	142.5	0.2 pcf	X	

From Section 9-34 - Table 2 (TM529) --- Allowable Density Difference (between technicians) **1.50 pcf**

If Diff. ≤ 1.50 pcf, then Acceptable
If Diff. > 1.50 pcf, then Unacceptable

Section 15 - 15

15